

SIO-2® Aneto - White Porcelain Clay

WHY CHOOSE SIO-2® ANETO?

SIO-2® Aneto has been formulated for both artistic ceramics and pottery, it offers exceptional plasticity for intricate modeling and dinnerware.

IS SIO-2® ANETO CLAY MICROWAVE SAFE?

Yes, your SIO-2® Aneto dinnerware can be safely heated in the microwave.

IS SIO-2® ANETO SUITABLE FOR TABLEWARE?

Yes. SIO-2® Aneto clay bodies are food-safe according to ISO 6486:1999 standards.

GLAZE RECOMMENDATIONS


SIO-2® Aneto clay works well with most liquid glazes. It is recommended to test fire a small object before applying to larger sculptures or dinnerware.



ANETO Corrie Bain



ANETO Rosa Cortiella



Cone 5

Cone 6

Cone 8

SIO-2® Aneto is known for its pure white color, fine grain size, and exceptional strength and durability. Fires to a translucent white porcelain that stands out for its high plasticity, which makes it exceptional for wheel-throwing and modeling.

SIO-2® Aneto is suitable for producing delicate and intricate pieces, such as fine china, porcelain figurines, and other decorative items.

It has been formulated for use in both artistic ceramics & pottery, boasting exceptional plasticity that makes it perfect for intricate modeling or dinnerware.

Firing range: Cone 6-8 (2269°F - 2320°F)
Biscuit temperature: Cone 06 (1855°F)
Water content: 21%
Plasticity (IP Atterberg): 11
Carbonate content (CaCO₃): 0%
Drying shrinkage: 4.0%
Firing shrinkage at Cone 7: 9.8%
Porosity (water absorption at Cone 7): 0.0%
Dry bending strength: 3.1 N/mm²
Fired bending strength at Cone 7: 45.2 N/mm²
Thermal coefficient (25-500°C): 59.2x10⁻⁷°C⁻¹



info@sandtastik.com
P: 905-734-7340
F: 905-734-7733
www.sandtastik.com