

SIO-2® PF – Red Earthenware Clay

WHY CHOOSE SIO-2® PF CLAY?

This low firing clay has a distinctive red color and texture. Its high plasticity makes it a great choice for potters who want to create pieces with intricate designs and details.

IS SIO-2® PF CLAY MICROWAVE SAFE?

PF clay should be microwave safe if it was covered in a non-porous glaze (however to ensure the longevity of your objects, it's always better to avoid using them in the microwave or dishwasher).

IS SIO-2® PF SUITABLE FOR TABLEWARE?

Yes. PF clay bodies are food-safe according to ISO 6486:1999 standards.

GLAZE

RECOMMENDATIONS

SIO-2® PF clay is highly versatile and can be glazed with any standard glaze, in both single and twice firing processes.



PF Naharro



PF Ceramiques Sedo



SIO-2® PF is a red earthenware clay that is prized for its fine quality and plasticity. It can be used for a variety of applications including wheel-throwing, modelling, and shaping.

It is a traditional and highly versatile clay that has ideal coefficients of thermal expansion, which make it suitable for use with standard pottery glazes.

SIO-2® PF Clay has a shrinkage rate of just 5.5%, allowing for precise control over the size and shape of your pieces.

This clay can produce amazing results using the metallic reflection technique in a reduced oxygen atmosphere. Its smooth texture and rich color make it a joy to work with, and its low firing range makes it accessible to artists of all skill levels.



Firing range: Cone 06-04 (1155°-1971°F)

Water content: 22%

Plasticity (IP Atterberg): 17

Carbonate content (CaCO₃): 10%

Drying shrinkage: 5.5%

Firing shrinkage at Cone 06: 0.6%

Porosity (water absorption) at Cone 06: 13.5%

Dry bending strength: 6.6 N/mm²

Fired bending strength at Cone 06: 27.9 N/mm²

Thermal coefficient (a_{25-500°C}):

77.7x10⁻⁷°C⁻¹



info@sandtastik.com
P: 905-734-7340
F: 905-734-7733
www.sandtastik.com